



# LNE

Le progrès, une passion à partager

LABORATOIRE DE TRAPPES  
29 avenue Roger Hennequin – 78197 Trappes Cedex  
Tél. : 01 30 69 10 00 – Fax : 01 30 69 12 34

File G110139- Document CEMATE/3 - Page 1/4

## EUROPEAN REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO THE EUROPEAN STANDARD EN 13501-1

Notified Body by the French State besides the European Commission under number : 0071

Product standard : NF EN 14904  
Specification for indoor surfaces for multi-sports use

(free translation of French classification report n° G110139 CEMATE/2)

**N°G110139 - CEMATE/3**

**Material submitted by :** DALSOUPLE  
152 rue Flandre Dunkerque  
BP81  
49403 SAUMUR CEDEX  
FRANCE

**Commercial trademark :** DALSOUPLE LISSE et RELIEFS

**Brief description :** Rubber floorcovering

**Date of report :** 2007, March 16<sup>th</sup>

**Only full reproduction of the present document is authorized.  
It contains 4 pages**

### Laboratoire national de métrologie et d'essais

Établissement public à caractère industriel et commercial • Siège social : 1, rue Gaston Boissier - 75724 Paris Cedex 15 • Tél. : 01 40 43 37 00  
Fax : 01 40 43 37 37 • E-mail : info@lne.fr • Internet : www.lne.fr • Siret : 313 320 244 00012 • NAF : 743 B • TVA : FR 92 313 320 244  
Barclays Paris Centrale IBAN : FR76 3058 8600 0149 7267 4010 170 BIC : BARCFRPP

## 1. INTRODUCTION

This classification report defines the classification assigned to product in accordance with the procedures given in EN 13501-1.

## 2. DETAILS OF CLASSIFIED PRODUCT

### 2.1. NATURE AND END USE APPLICATION

Resilient floor covering.

### 2.2. DESCRIPTION

Product characteristics:

Trademark	Composition	Mass per unit square meter	Thickness
DALSOUPLE LISSE et RELIEFS	Rubber Mineral loads Antioxidant Plasticizers Colour additives	1,6 kg/m <sup>2</sup> /mm of thickness	2 mm; 3,5 mm; 4 mm

Fireproofing : no

*Informations given by the sponsor*

Text report to be followed on next page

### 3. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

#### 3.1. TEST REPORTS

Name of laboratory	Name of sponsor	Test report ref. n°	Test method
Laboratoire national de métrologie et d'essais 29 av. Roger Hennequin 78197 TRAPPES CEDEX	DALSOUPLE 152 rue Flandre Dunkerque BP81 49403 SAUMUR CEDEX FRANCE	File : G110139 CEMATE/1	Radiant panel EN ISO 9239-1

#### 3.2. TEST RESULTS FOR FLOORINGS

Test method	Number of tests	Parameters	Results
NF EN ISO 9239-1 Glued on A1 classified substrate	1 (4 specimens)	Critical flux (kW/m <sup>2</sup> ) Smoke (%.min)	9.41 121

Text report to be followed on next page

#### 4. CLASSIFICATION AND DIRECT FIELD APPLICATION

##### 4.1. CLASSIFICATION

Fire behaviour	Smoke production	Flaming droplets
<b>B<sub>fl</sub></b>	<b>S1</b>	-

##### 4.2. FIELD OF APPLICATION

This classification is valid for the products mentioned in § 2.2 or strictly and equally stipulated in the quoted production site.

Colour : various

Glued on A1 and A2 classified substrate.

#### 5. LIMITATIONS

##### 5.1. RESTRICTIONS CONCERNING THE VALIDITY PERIOD OF THE CLASSIFICATION REPORT

None.

##### 5.2. WARNING

This document does not represent type approval or certification of the product.

Trappes, the 16<sup>th</sup> of March 2007

The Head of Fire Behaviour Division

Test officer



Alain SAINRAT



Luc CHEVALIER