

DALSOUPLE CHEMICAL RESISTANCE DATA

Test of resistance to chemical testing agents

Testing agent		After 2 minutes	1 hour
Sulphuric acid	30%	No effect	No effect
Acetic acid	5%	No effect	No effect
Citric acid	5%	No effect	No effect
Lactic acid	5%	No effect	No effect
Hydrogen peroxide	30%	No effect	No effect
Hydrochloric acid	20%	No effect	No effect
Ammonia solution	25%	No effect	No effect
Sodium hydrochloride	25%	No effect	No effect
Solution of Phenol	10%	No effect	No effect
Sodium hydroxide	50%	No effect	No effect
Sodium carbonate	20%	No effect	No effect
Nitric acid	30%	No effect	Loss of gloss
Formaldehyde	3%	No effect	No effect
Turpentine		No effect	Loss of gloss (minimal)
Ethanol		No effect	No effect
Acetone		No effect	No effect
Mineral oil		No effect	No effect
Ether		No effect	No effect
Benzine		No effect	Loss of gloss (minimal)

Dalsouple, Showground Road, Bridgwater, Somerset, England TA6 6AJ
Telephone: +44(0)1278 727777 Fax: +44(0)1278 727788
info@dalsouple.com www.dalsouple.com